

TECHNICAL DATA SHEET

DESCRIPTION

Sure Bond J58 LPL is a 100% solids, two component, high modulus, medium viscosity, moisture tolerant, long open time structural epoxy adhesive.

USE

Sure Bond J58 LPL primary use is for bonding fresh concrete to hardened concrete or steel. Sure Bond J58 LPL has excellent adhesion to most construction materials.

FEATURES

- High strength structural adhesive meeting ASTM C-881 and AASHTO M-235
- Ideal for bonding fresh concrete to hardened concrete
- Very long open time
- Moisture tolerant
- Excellent adhesion to most materials

PROPERTIES

Meets Specifications: ASTM C-881, AASHTO M-235, Types I, II, & V, Grade 2, Classes B & C

Mix ratio: 2:1, part A to part B by volume

Color (mixed): Gray

Brookfield Viscosity (ASTM C-881): 6,300 cps

Gel times: 3.5 hours @ 73°F (23°C)

Compressive Yield Strength (ASTM D-695): 9,000 psi (62 MPa) @ 7 days

Compressive Modulus (ASTM C-695): 255,000 psi (1,758.2 MPa) @ 7 days

Concrete Bond Strength (ASTM C-882): 2 days 1,500 psi (10.3 MPa)

Tensile strength (ASTM D-638): 6,500 psi (44.8 MPa)

Elongation at break (ASTM D-638): 6.5%

Flexural Strength (ASTM D-790): 8,500 psi (58.6 MPa) (

Heat Deflection (ASTM D-648): 122 degrees F (50 C)

Water Absorption (ASTM D-570): 0.75%

Shrinkage (ASTM C883): Passes

Thermal Compatibility (ASTM C-884): Passes

VOC

Sure Bond J58 LPL has a VOC content of 0 g/L. Compliant with all Canadian and U.S. VOC regulations including Federal EPA, OTC, LADCO, SCAQMD & CARB.

Estimating Guide

Apply Sure Bond J58 LPL at a thickness of approximately 20 mils (80 sq. ft./gal., 1.96 sq. M/L).

Packaging

PRODUCT CODE	PACKAGE	SIZE	
		Gallons	Liters
143336	Unit	1	3.79
309332	Unit	3	11.36
139885	Unit	15	56.78

STORAGE

The material should be stored at 40°-95°F (5°-35°C). Shelf life of properly stored, unopened containers is 24 months.

APPLICATION

Surface Preparation:

Surface to be bonded must be clean and sound. Remove oil, dirt, grease, laitance, curing compounds and other foreign matter that may cause a problem with bond. Abrasive blast cleaning and mechanical removal methods are recommended.

Mixing:

Condition material to 65°- 85°F (18°- 29°C) before using. Premix each component then place 2 parts by volume of Component A and 1 part by volume of component B into a clean pail and mix for three minutes with a low speed drill using a Jiffy mixer or paddle until uniformly blended. Mix only what can be used within the pot life. Air, material, and surface temperatures must be 50°F (10°C) prior to mixing or installation.

Placement:

For bonding fresh concrete to hardened concrete, apply the Sure Sure Bond J58 LPL material neat by brush, roller or spray and work into substrate. While the Sure Bond J58 LPL is still tacky, place the fresh concrete.

CLEAN UP

Tools and Equipment: Clean before the epoxy sets. Use xylene or Dayton Superior Citrus Cleaner J48. Cured material can only be removed mechanically.

LIMITATIONS

FOR PROFESSIONAL USE ONLY

Minimum age of concrete must be 21-28 days from date of placement depending on curing and drying conditions. If the Sure Bond J58 LPL is no longer tacky during bonding operations, and within 16 hours after application of the bonder, clean and solvent wipe the area and re-apply the Sure Bond J58 LPL.

TECHNICAL DATA SHEET

If more than 16 hours has lapsed since application, the area must be lightly sanded or abraded and solvent wiped clean prior to re-application of the Sure Bond J58 LPL. Do not thin with any solvents. Surface, ambient air, and material temperatures must be 50°F (10°C) or above. Note: High temperatures will accelerate the setting time and cool temperatures will slow the setting time. As a general rule, the gel time of the epoxy will be cut in half for each 10° to 15° increase in temperature above 75°F (24°C).

PRECAUTIONS

READ SDS PRIOR TO USING PRODUCT

- Component A – Irritant
- Component B – Corrosive
- Product is a strong sensitizer
- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (goggles, safety glasses and/or face shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately
- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements
- Cured epoxy resins are innocuous

MANUFACTURER

Dayton Superior Corporation
1125 Byers Road
Miamisburg, OH 45342
Customer Service: 888-977-9600
Technical Services: 877-266-7732
Website: www.daytonsuperior.com

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.