

TECHNICAL DATA SHEET

DESCRIPTION

Pro-Poxy™ AWP is a high solids, low modulus, three-component, all weather, non-shrinking epoxy/urethane hybrid concrete repair and patching material. Pro-Poxy™ AWP utilizes high solids epoxy/urethane technology along with specialty graded aggregates for achieving rapid turn around concrete repairs in all weather conditions.

USE

Pro-Poxy AWP is specifically formulated, designed and engineered for use as an all weather, interior/exterior concrete spall and crack patching and repair mortar where a rapid turn around time is critical or cold conditions are a concern. Pro-Poxy AWP can be used for patching of bridge decks, overpasses and roadway surfaces, freezers and cold room floors, airport runways, warehouse floors and any concrete slab or floor traffic way in need of repair or patching where cold temperatures are present or rapid turn around time is required.

FEATURES

- Non-shrink
- Chemical resistant
- Easy 1:1 mixing ratio for Parts A & B
- Cures in temperatures as low as -20°F (-29°C)
- Open to traffic within 20 minutes
- Meets FDA and USDA requirements
- Low odor

PROPERTIES

Color: Medium gray
 Viscosity (mixed neat): 250 cps
 Gel Time (100g mass): 3 minutes @ 73°F (23°C)
 ASTM D638:
 Tensile elongation: >30%
 Tensile strength: >2000 psi
 ASTM C579 Compressive Strength:
 1 hour: 2,216 psi
 3 hour: 2,583 psi
 24 hour: 3,416 psi

VOC

Product has a VOC content of 0 g/L. Compliant with all Canadian and U.S. VOC regulations including Federal EPA, OTC, LADCO, SCAQMD & CARB.

Estimating Guide

Yield: 1 unit yields 0.45 cu. ft. (0.013 cu. m)

Packaging

| PRODUCT CODE | PACKAGE | SIZE | |
|--------------|---------|--------|-------|
| | | cu. ft | cu. m |
| 140502 | Unit | .45 | 0.013 |

STORAGE

Pro-Poxy AWP should be stored in a dry temperature controlled environment between 50°F to 85°F (10°C to 29°C). Do not store in direct sunlight. Shelf life is 1 year if cans are unopened, undamaged, and stored properly

Surface Preparation:

Pro-Poxy AWP is moisture sensitive and should not be applied to wet surfaces. New concrete must be a minimum of 28 days old and dry at the time of installation. Clean the area of all debris and contaminants; oil, grease, dust, dirt, unsound concrete etc. Expose clean roughened concrete for best results. Cut or chip a vertical edge, minimum ½ in. (1.3 cm) deep, around perimeter of the area to be patched. Make sure the area is clean dry and sound. Sandblasting may be necessary to expose clean concrete. Vacuum or blow off concrete dust and debris with oil-free compressed air.

Mixing:

For temperatures below 10°F (-12.20C) kit contents should be preconditioned to 65°F - 85°F (18.30 - 29.40C). Have all components and tools ready and patch area properly prepared prior to mixing/placement. Mixing container, tools and patch area must be clean and dry prior to use. Mix only as much Pro-Poxy AWP as can be used within the pot life of the material approximately 3-5 minutes at room temperature. Stir/shake each component A & B for 30 seconds. Mix each component A & B together for 30 seconds then add component C aggregate and mix for an additional 30 seconds until all of the aggregate is wetted out. PLACE IMMEDIATELY. MIXING LESS THAN FULL KIT QUANTITIES: Shake component B for 30 seconds. Mix equal parts (1:1 ratio) of components A and B vigorously for 30 seconds. Add 3 parts by volume of component C to 1 part mixed A & B components and stir for 30 seconds until aggregate is wetted out. PLACE IMMEDIATELY.

TECHNICAL DATA SHEET

Placement:

Pour and place the Pro-Poxy AWP immediately after mixing. Use a clean steel trowel to force the Pro-Poxy AWP down into the repair area and then to strike off the top surface to match the surrounding concrete. Steel trowels may be slicked off using Xylene to add a degree of lubricity to troweling and cleaning off the trowel surface. After reaching set in about 20 minutes, the Pro-Poxy AWP may be ground flat and level with the surrounding concrete using a flexible 7 in. (17.8 cm) grinding wheel to grind smooth and level with the finished grade. Pro-Poxy AWP may also be shaped by scraping or cutting with a razor knife scraper before reaching full set.

CLEAN UP

Clean tools with Xylene or Acetone before the material has set. Excess Part A and Part B material should be mixed together and allowed to reach hard set, then discarded in the hardened form.

LIMITATIONS

FOR PROFESSIONAL USE ONLY

For temperatures below 10°F (-12.20C) kit contents should be preconditioned to 65°F - 85°F (18.30 - 29.40C). Temperature of the substrate must be above -20°F (-28.9°C) during installation and for initial cure period. Pro-Poxy AWP is moisture sensitive and should not be installed on wet or damp concrete.

PRECAUTIONS

READ SDS PRIOR TO USING PRODUCT

- Component A – Irritant
- Component B – Corrosive
- Component “C” Irritant: Contains Portland cement.
- Product is a strong sensitizer
- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (goggles, safety glasses and/or face shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately
- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.

- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements
- Cured epoxy resins are innocuous

MANUFACTURER

Dayton Superior Corporation
1125 Byers Road
Miamisburg, OH 45342
Customer Service: 888-977-9600
Technical Services: 877-266-7732
Website: www.daytonsuperior.com

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

TECHNICAL DATA SHEET

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.