



## Product Selection Guide

### Repair Mortars

Product Name	Depth of Placement			Extension (Pea Gravel)	Corrosion Inhibitor	Shrinkage Compensated	Latex/Polymer Modified	Epoxy Based	Vertical / Overhead	Horizontal	Form/Pour	Notes
	Min.	Max. Neat	Max Extended									
Polyfast FS	1/4"	2" per lift	4"	15lbs								
Recrete 5 Minute	1/8"	2" per lift	4"	25lbs								
Recrete 20 Minute	1/8"	2" per lift	4"	25lbs								
Recrete Light 20	1/8"	2" per lift	4"	25lbs								
Architectural Finish	Feather	1/8"	NA	NA								
Perma Patch VO	1/4"	2" per lift	NA	NA								
HD 25 VO	1/4"	2" per lift	4"	15lbs								#4,8
Civil/Structural VO	3/8"	2" per lift	NA	NA								#1,4
Civil/Structural FPX	1"	12"	NA	NA								#2
Perma Patch FP	1/4"	2"	4"	15-30lbs								#2
Thin Resurfacer	Feather	1/2"	NA	NA								#3
Special Patch	1/8"	2" per lift	4"	30#								
HD 50	1/2"	2" per lift	6"	30lbs								#2,4,5,8
Pave Patch 3000	1/2"	2" per lift	6"	30lbs								#2,5
DOT Rapid Repair	1/2"	2" per lift	8"	30lbs								
Rapid Resin Repair	1/2"	3"	NA	NA								#6
Sure Patch	1/2"	3"	6"	50%								#7
ProPatch VO	1/4"	2"	NA	NA								

*Blue cells indicate that the description or specification applies to the product.*

**Notes:**

1. Silica fume enhanced. Can be applied by low velocity spray
2. Excellent for Form & Pump and Form & Pour
3. Minimum depth of 1/8" for improved performance
4. Fiber enhanced
5. Excellent for Dowel Bar Retrofit Mortar
6. Cures in temperatures as low as -20°F (-29°C)
7. Low modulus repair mortar for interior/exterior repairs
8. Calcium Aluminate-based