

TECHNICAL DATA SHEET

DESCRIPTION

Cure Hard J14 is a ready-to-use, water-based general purpose curing aid designed to help ensure proper concrete strength development. Cure Hard J14 will not interfere with future flooring adhesives, coatings, treatments or flooring materials.

USE

Cure Hard J14 is ideal as a curing aid or can be used for hardening and dustproofing of interior and exterior, horizontal and vertical concrete surfaces.

FEATURES

- Helps prevent plastic shrinkage cracks
- Non-flammable/odorless/VOC Compliant
- Penetrates to aid curing
- May contribute to LEED credits
- Will not inhibit adhesion of secondary coatings, topping, or adhesives
- Certified to NSF/ANSI 61 by WQA
- Tested and compliant per CDPH V1.2



Drying time:

Approximately 1 hour at 70°F (21°C).
Allow treated area to dry before opening to traffic.
Dry time is temperature, humidity and wind dependent.

VOC

"0" g/L. Compliant with all Canadian and U.S. VOC regulations for including Federal EPA, OTC, LADCO, SCAQMD & CARB.

Estimating Guide

Surfaces to receive flooring, densifiers or adhesive should be treated at the Trowel Finish coverage rate.

Broom finish 200 – 400 Ft²/Gallon 4.9 – 9.8 M²/Liter
Trowel finish 500 – 600 Ft²/Gallon 12 – 14.8 M²/Liter.

Texture and absorption characteristics of the surface will dictate final coverage rates.

Packaging

Product Code	Packaging	Size	
		Gallon	Liter
146531	Pail	5	18.9
146532	Drum	55	208.2

STORAGE

Keep from freezing. Shelf life is 24 months from date of manufacture in original unopened containers.

Surface Preparation:

Freshly finished concrete surfaces require no surface preparation, applied immediately after the bleed water has dissipated or after final finishing. On older concrete, substrate must be absorptive. Remove all oil and grease, paint and coatings to assure penetration and hardening.

Mixing

Mix thoroughly prior to each use.

Placement:

Apply only when temperatures are above 40°F (4°C). When used as a cure aid, apply with a low pressure sprayer once the surface is dry to the touch or hard enough to walk on. Remove excess material and puddles from surface with a broom or squeegee. On existing concrete, apply with a low pressure sprayer, soft bristle broom, brush or squeegee. For optimum hardening, apply two coats. Remove excess material and puddles from surface after application is complete.

CLEAN UP

Tools and equipment use clean, fresh water. After the product dries, hot water scrubbing or sanding may be required for removal.

LIMITATIONS

This product is certified to conform to NSF/ANSI Standard 61 at a maximum surface area to volume ratio of 98.4 sq. cm/L.

PRECAUTIONS

Will stain glass, metal and other trim. Protect from contact. Clean accidental splash or spill immediately with water.

During rapid drying conditions such as low humidity, low dew point, high winds, direct sunlight and hot weather use AquaFilm J74RTU to minimize moisture loss during finishing.

In such conditions consider using a curing compound with a lower moisture loss.

TECHNICAL DATA SHEET**PRECAUTIONS****READ SDS PRIOR TO USING PRODUCT**

- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (goggles, safety glasses and/or face shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately
- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements

MANUFACTURER

Dayton Superior Corporation
1125 Byers Road
Miamisburg, OH 45342
Customer Service: 888-977-9600
Technical Services: 877-266-7732
Website: www.daytonsuperior.com

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.