

TECHNICAL DATA SHEET

DESCRIPTION

Cure & Seal 25% Brown is an acrylic copolymer cure, seal and dustproofing compound in an aromatic solvent containing 25% solids with special U.V. stabilizers. The higher acrylic solids content will form an excellent surface coating with a high gloss brown tinted finish for exposed aggregate concrete that will provide an outstanding cure performance. The translucent brown color will highlight the color of the exposed aggregate. Cure & Seal 25% Brown is ultraviolet light stable and resists yellowing.

USE

Cure & Seal 25% Brown provides a combination curing, sealing and dustproofing and translucent brown tint for freshly finished exposed aggregate concrete surfaces. It meets the ASTM C-309 & ASTM C-1315 specifications as an outstanding curing compound and is an excellent dustproofer and surface sealer.

FEATURES

- High solids content
- Cures (Meets ASTM C-309)
- Cure & Seals (Meets ASTM C-1315)
- Dustproofs
- U.V. Stable, resists yellowing
- Translucent brown finish

PROPERTIES

ASTM C-309, Type 1, Classes A & B
ASTM C-1315, Type 1, Class A

Drying time:

Approx. 2 hours at 70°F (21°C) for recoating or light traffic. Wait 12 hours for heavy traffic. Dry time is temperature, humidity and wind dependent.

VOC

Complies with U.S. EPA requirement less than 700 g/L

Estimating Guide

Coverage Rates:

1st coat 200 – 400 Ft²/Gallon 4.9 – 9.8 M²/Liter

2nd coat 400 – 600 Ft²/Gallon 9.8 – 14.8 M²/Liter

Texture and absorption rate of the concrete will influence coverage rate.

Packaging

PRODUCT CODE	PACKAGE	SIZE	
		Gallons	Liters
202622	Can	1	3.7
202621	Pail	5	18.9

STORAGE

Cure & Seal 25% Brown should be stored in tightly sealed original factory containers. Shelf life of properly stored, unopened containers is 24 months. Store in a temperature range between 0°F (-18°C) to 110°F (43°C).

Mixing:

Pigments may settle. Mix well before each use.

Placement:

Apply Cure & Seal 25% Brown immediately after all surface water has disappeared and the surface cannot be marred. Application of Cure & Seal 25% Brown too early or too late can affect the overall curing performance. Use low pressure spray, roller or brush. Make sure that the sprayer, as well as any other equipment that the material will come into contact with is clean and dry. Do not contaminate the Cure & Seal 25% Brown with other materials, solvents, or water. Do not thin. Apply uniformly without puddles.

CLEAN UP

Clean tools and equipment with Xylol or lacquer thinner while product is still wet. Dried material may be removed with Dayton Superior Green Bean Clean®.

LIMITATIONS**FOR PROFESSIONAL USE ONLY**

Not intended for application in enclosed or interior spaces. For applications of a cure and seal in an enclosed structure, Dayton Superior recommends a water based product like the Cure & Seal 309 EF or Cure & Seal 1315 EF. Do not apply at temperatures below 40°F (4 °C) or when the average daily temperature remains below 40°F (4°C). Sprayers and equipment must have suitable type solventresistant hoses and gaskets. Do not apply concrete or mortar toppings over sealed surfaces. Remove Cure & Seal 25% Brown before applying resinous (epoxy, polyester, urethanes, etc.) coatings. Do not store food containers directly on the floor, always place on pallets.

TECHNICAL DATA SHEET

PRECAUTIONS**READ SDS PRIOR TO USING PRODUCT**

- Keep material and containers away from high heat, open flames, sparks or other sources of ignition
- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (goggles, safety glasses and/or face shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately
- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements

MANUFACTURER

Dayton Superior Corporation
1125 Byers Road
Miamisburg, OH 45342
Customer Service: 888-977-9600
Technical Services: 877-266-7732
Website: www.daytonsuperior.com

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.