

TECHNICAL DATA SHEET

DESCRIPTION

Cure & Seal 1315 J22WB is a water based acrylic copolymer containing 25% solids that offers outstanding curing, sealing and dustproofing for freshly finished concrete surfaces. The high solids content will form a long lasting surface membrane with a high gloss finish that will provide excellent cure performance. This product dries to produce a non-yellowing, durable, clear film on concrete. Cure & Seal 1315 J22WB is ideal for interior applications because it is free of noxious fumes and it is nonflammable.

USE

Cure & Seal 1315 J22WB is a convenient, safe to use product that surpasses the ASTM C-309 & ASTM C 1315 specifications as a superb membrane forming curing compound and it is an excellent dustproof and surface sealer.

FEATURES

- Water-based
- High solids content
- High gloss sealer and dustproof
- Low odor, ideal for interior applications
- Non-flammable
- Easy clean up with water
- Interior/exterior

PROPERTIES

ASTM C-309, Type 1, Class A & B
 AASHTO M-148, Type 1, Class A & B
 ASTM C-1315, Type 1, Class A

Drying time:

Approximately 2-3 hours at 70°F (21°C) for recoating or light traffic.
 Wait 12 hours for heavy traffic.
 Dry time is temperature, wind and humidity dependent.

VOC

Less than 350 g/l. Complies with Canadian and U.S. Federal EPA, OTC CARB & LADCO Standards for Concrete Curing Compounds

Estimating Guide

Coverage Rates:
 1st coat 200 – 400 Ft²/Gallon 4.9 – 9.8 M²/Liter
 2nd coat 400 – 600 Ft²/Gallon 9.8 – 14.8 M²/Liter
 Texture and absorption rate of the concrete will influence coverage rate.

Packaging

PRODUCT CODE	PACKAGE	SIZE	
		Gallons	Liters
307919	Pail	5	18.93
307918	Drum	55	208.20

STORAGE

The Cure & Seal 1315 J22WB should be stored in tightly sealed original factory containers. Store in a horizontal position to prevent moisture accumulation on the drum head. Do not allow to freeze. Shelf life of properly stored, unopened containers is 1 year

APPLICATION

Apply when all free water has disappeared and surface cannot be marred. Do not delay in applying Cure & Seal 1315 J22WB. Use low-pressure spray, roller or brush. Do not thin. Apply uniformly without puddles. For improved application consistency and reduction in labor use the Dayton Spray-Pro (Item # 309233 or 309232) power spray system. The second coat, which is optional, will provide a longer lasting surface coating with a higher gloss finish.

Mixing:

Agitate Cure & Seal 1315 J22WB before each use.

CLEAN UP

Clean tools and equipment with clean water while product is still wet. Dried material may be removed with Green Bean Clean or Citrus Cleaner J48

LIMITATIONS

FOR PROFESSIONAL USE ONLY

This product should not be used at temperatures below 40°F (4°C). Do not apply concrete or mortar toppings over sealed surfaces. Avoid spraying Cure & Seal 1315 J22WB into joint prior to installation of sealant. May show rubber tire marks. Do not use high speed mixing equipment. Remove Cure & Seal 1315 J22WB with Citrus Cleaner J48 or Green Bean Clean® before applying resinous (epoxy, polyester, urethanes, etc.) coatings. Do not store food containers directly on the floor, always place on pallets. When moisture-sensitive flooring is to be applied to the concrete treated with this product first refer to ACI 302.2R

PRECAUTIONS

READ SDS PRIOR TO USING PRODUCT

- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (goggles, safety glasses and/or face shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately

TECHNICAL DATA SHEET

- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements

MANUFACTURER

Dayton Superior Corporation
1125 Byers Road
Miamisburg, OH 45342
Customer Service: 888-977-9600
Technical Services: 877-266-7732
Website: www.daytonsuperior.com

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.