

## TECHNICAL DATA SHEET

### DESCRIPTION

Slow Set Bonding Agent is a 100% solids, two component, high modulus, medium viscosity, moisture tolerant, long open time structural epoxy adhesive meeting the requirements of ASTM C-881 and AASHTO M-235. Slow Set Bonding Agent with its slower cure rate, may be used in temperatures between 60°F and 110°F (16°C and 43°C)

### USE

Slow Set Bonding Agent primary use is for bonding fresh concrete to hardened concrete or steel. Slow Set Bonding Agent has excellent adhesion to most construction materials.

### FEATURES

- Acceptable for use in USDA inspected facilities
- Ideal for bonding fresh concrete to hardened concrete
- Secondary use for anchoring dowels, bolts and reinforcing steel
- Medium viscosity pumpable formula
- Moisture tolerant
- Excellent adhesion to most materials

### PROPERTIES

Slow Set Bonding Agent - Type I, II, IV\*, & V\*\* Grade 2 Class C. \*With exception of tensile strength; \*\*Approved at temperatures greater than 75 °F (24 °C); Acceptable for use in USDA inspected facilities.

### VOC

Slow Set Bonding Adhesive has a VOC content of 0 g/L and is compliant with all Canadian and U.S. VOC regulations including Federal EPA, OTC, LADCO, SCAQMD & CARB.

### Estimating Guide

Apply Slow Set Bonding Agent at a thickness of approximately 20 mils (80 sq. ft./gal., 1.96 sq. M/L).

### Packaging

PRODUCT CODE	PACKAGE	SIZE	
		Gallons	Liters
140434	Unit	2	9.1

### STORAGE

The material should be stored at 40° -95°F (5° -35°C). Shelf life of properly stored, unopened containers is 24 months.

### Surface Preparation:

Surface to be bonded must be clean and sound. Remove oil, dirt, grease, laitance, curing compounds and other foreign matter that may cause a problem with bond. Abrasive blast cleaning and mechanical removal methods are recommended.

### Mixing

Condition material to 65°- 85°F (18°- 29°C) before using. Premix each component then place 1 part by volume of Component A and 1 part by volume of component B into a clean pail and mix for three minutes with a low speed drill using a Jiffy mixer or paddle until uniformly blended. Mix only what can be used within the pot life. Air, material, and surface temperatures must be 50°F (10°C) prior to mixing or installation.

### Placement:

For bonding fresh concrete to hardened concrete, apply the Slow Set Bonding Agent material neat by brush, roller or spray and work into substrate. While the Slow Set Bonding Agent is still tacky, place the fresh concrete.

### CLEAN UP

Tools and Equipment: Clean before the epoxy sets. Use xylene or Unitex Citrus Cleaner. Cured material can only be removed mechanically.

### LIMITATIONS

#### FOR PROFESSIONAL USE ONLY

Minimum age of concrete must be 21-28 days from date of placement depending on curing and drying conditions. Not recommended for any anchoring and doweling application where there may be a sustained tensile load, including overhead applications. If the Slow Set Bond Adhesive is no longer tacky during bonding operations, and within 16 hours after application of the bonder, clean and solvent wipe the area and re-apply the Slow Set Bond Adhesive. If more than 16 hours has lapsed since application, the area must be lightly sanded or abraded and solvent wiped clean prior to re-application of the Slow Set Bond Adhesive.

Do not thin with any solvents

Note: High temperatures will accelerate the setting time and cool temperatures will slow the setting time. As a general rule, the gel time of the epoxy will be cut in half for each 10° to 15° increase in temperature above 75°F and the gel time will double for each 10° to 15° drop below 75°F (24°C).

**TECHNICAL DATA SHEET****PRECAUTIONS****READ SDS PRIOR TO USING PRODUCT**

- Component A – Irritant
- Component B – Corrosive
- Product is a strong sensitizer
- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (goggles, safety glasses and/or face shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately
- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements
- Cured epoxy resins are innocuous

**MANUFACTURER**

Dayton Superior Corporation  
1125 Byers Road  
Miamisburg, OH 45342  
Customer Service: 888-977-9600  
Technical Services: 877-266-7732  
Website: [www.daytonsuperior.com](http://www.daytonsuperior.com)

**WARRANTY**

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.

## TECHNICAL DATA SHEET

### Appendix A

TABLE 1: Slow Set Bonding Agent Performance to ASTM C881-20a<sup>1,2,3</sup>

Property	Cure Time	ASTM Standard	Units	Sample Conditioning Temperature
				Class C <sup>4</sup>
				75 °F (24 °C)
Gel Time – 60 Gram Mass	----	C881	Min	126
Compressive Yield Strength	7 day	D695	PSI (MPa)	11,800 (81.4)
Compressive Modulus			PSI (MPa)	688,000 (4,743)
Viscosity	----	C881	cP	5,050
Bond Strength Hardened to Hardened Concrete	2 day	C882	PSI (MPa)	2,500 (17.2)
	14 Day		PSI (MPa)	2,690 (18.5)
Bond Strength Fresh to Hardened Concrete				PSI (MPa)
Heat Deflection Temperature	7 days	D648	°F (°C)	129 (53.9)
Water Absorption	24 Hours	D570	%	0.1
Linear Coefficient of Shrinkage	----	D2566	%	0.001
Tensile Strength	7 day	D638	PSI (MPa)	6,200 (42.7)
Tensile Elongation	7 day	D638	%	1.2

1. Results based on testing conducted on a representative lot(s) of product. Average results will vary according to the tolerances of the given property.

2. Full cure is listed above to obtain the given properties for each product characteristic.

3. Results may vary due to environmental factors such as temperature, moisture and type of substrate.

4. Class C is applicable from temperatures of 75 °F (24 °C) to 110 °F (43 °C).

Not recommended for any anchoring and doweling application where there may be a sustained tensile load, including overhead applications.